

TEADIT GR 1520

graphite sheet with plain metal insert SS 316

Material composition:

TEADIT expanded graphite sheets are produced from pure, expanded flexible graphite and do not contain any other fibers or filler materials.

Properties:


TEADIT expanded flexible graphite sheets are universally applicable for gases and fluids. They are chemically resistant against most media, have excellent thermal conductivity, can be stored indefinitely, do not need anti-stick coating and are extremely resistant to temperature cycles.

Application areas:

Because of its specific structure expanded graphite sheets are particularly suited for applications with extremely high or low temperatures, with highly corrosive and aggressive media, for sensitive flange materials (i.e. enamel, glass, plastic) and for gas and steam applications.

Technical data:

- Temperature range:- 240° C up to 450 ° C, with steam up to 650 °C, in non-oxidizing atmosphere up to 800°C
- pH range: 0 - 14
- pressure: 70 bar
- carbon content: > 98 %
- chloride content: < 30 ppm
- sulphur content: < 1000 ppm
- density (graphite): 1g/cm³
- compressibility: 40 - 50 %
- recovery: 10 - 25 %
- residual stress: > 45 N/mm²
- sheet size (in mm): 1.000 x 1.000
- thickness (in mm): 1.0 / 1.5 / 2.0 and 3.0



The following styles of TEADIT expanded graphite sheets are available :

- TEADIT GP 1520: pure expanded flexible graphite.
- TEADIT GE 1520/SS 304: pure expanded flexible graphite with tanged metal insert in SS 304 (0.1 mm)
- TEADIT GE 1520/SS 316: pure expanded flexible graphite with tanged metal insert in SS 316 (0.1 mm)
- TEADIT GR 1520: pure expanded flexible graphite with plain metal insert in SS 316 (0.05 mm)

Because graphite sheets are fragile and therefore difficult to handle, we recommend the use of styles with metal insertions. All styles are available with or without impregnation.

NO WAY THROUGH



TEADIT INTERNATIONAL
Rosenheimer Str. 10
6330 Kufstein
Tel.: +43-5372-64020-0
Fax: +43-5372-64020-20
austria@teadit.eu

TEADIT DEUTSCHLAND GmbH
Chemiepark G7/Raum 220
51368 Leverkusen
Tel.: +49-214-3023879
Fax.: +49-214-3023893
germany@teadit.eu

TEADIT ITALIA S.p.A.
Via Vanzago 13
25030 Paratico (BS)
Tel.: +39-035-924911
Fax: +39-035-913060
italy@teadit.eu

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences TEADIT® has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. TEADIT® does not undertake any liability of any kind whatsoever.